

**Grilamid XE 4106 black 9992**

PA612-GF30

EMS-GRIVORY | a unit of EMS-CHEMIE AG

**Product Texts**

Product-nomenclature according to ISO 1874:

PA612, MHR, 18-090, GF30

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	<b>9500 / 7500</b>	MPa	ISO 527-1/-2
Stress at break	<b>150 / 115</b>	MPa	ISO 527-1/-2
Strain at break	<b>4.5 / 6.5</b>	%	ISO 527-1/-2
Charpy impact strength (+23°C)	<b>90 / 90</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	<b>95 / 90</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	<b>15 / 16</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	<b>10 / 10</b>	kJ/m <sup>2</sup>	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	<b>185 / 145</b>	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	<b>215 / -</b>	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	<b>185 / -</b>	°C	ISO 75-1/-2
Temp. of deflection under load (8.00 MPa)	<b>110 / -</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	<b>30 / -</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	<b>100 / -</b>	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	<b>HB / -</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / -</b>	mm	IEC 60695-11-10
Max. usage temperature (long term)	<b>90 - 120</b>	°C	ISO 2578
Max. usage temperature (short term)	<b>180</b>	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	<b>1E10 / 1E10</b>	Ohm*m	IEC 60093
Surface resistivity	<b>- / 1E11</b>	Ohm	IEC 60093
Electric strength	<b>36 / 36</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>- / 600</b>	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	<b>2 / -</b>	%	Sim. to ISO 62
Humidity absorption	<b>0.9 / -</b>	%	Sim. to ISO 62
Density	<b>1300 / -</b>	kg/m <sup>3</sup>	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	<b>0.3 / -</b>	%	ISO 294-4, 2577
Molding shrinkage (normal)	<b>0.9 / -</b>	%	ISO 294-4, 2577

**Characteristics**

**Processing**

Injection Molding

**Product Attributes**

Hydrolysis resistant, Improved alcohol resistance

**Delivery form**

Granules

**Automotive**

Air intake systems, Compressed air systems, Hydraulic systems, Automotive electr. and electronics, lighting, Cooling and climate control, Fuel systems, Powertrain and Chassis , Interior, Exterior

**Grilamid XE 4106 black 9992**

PA612-GF30

EMS-GRIVORY | a unit of EMS-CHEMIE AG

**Special Characteristics**

Light stabilized or stable to light, Improved UV resistance (outdoor use), Improved heat resistance

**Regional Availability**

North America, Europe, Asia Pacific

**Electricals & Electronics**

Electrical appliances, Electrical equipment, Connectors, Lighting, Mobile phones and other portable devices

**Industry & Consumer goods**

Heating systems, Housewares, Hydraulics & Pneumatics, Mechanical Engineering, Power transmission, Sports & Leisure, Tools & Accessories

---