

**Grilon TSC-40/4 EC black 9832**

PA666-CF40

EMS-GRIVORY | a unit of EMS-CHEMIE AG

**Product Texts**

Product designation according to ISO 1874:

PA 66+PA 6, MHRS, 14-250 N, CF40

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	<b>26000 / 17000</b>	MPa	ISO 527-1/-2
Stress at break	<b>260 / 200</b>	MPa	ISO 527-1/-2
Strain at break	<b>2 / 4</b>	%	ISO 527-1/-2
Charpy impact strength (+23°C)	<b>60 / 85</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	<b>50 / 50</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	<b>10 / 16</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	<b>7 / 7</b>	kJ/m <sup>2</sup>	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	<b>190 / 110</b>	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	<b>260 / -</b>	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	<b>240 / -</b>	°C	ISO 75-1/-2
Temp. of deflection under load (8.00 MPa)	<b>185 / -</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	<b>10 / -</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	<b>70 / -</b>	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	<b>HB / -</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / -</b>	mm	IEC 60695-11-10
Max. usage temperature (long term)	<b>90 - 120</b>	°C	ISO 2578
Max. usage temperature (short term)	<b>200</b>	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	<b>100 / 100</b>	Ohm*m	IEC 60093
Surface resistivity	<b>- / 100</b>	Ohm	IEC 60093

Other properties	dry / cond	Unit	Test Standard
Water absorption	<b>5 / -</b>	%	Sim. to ISO 62
Humidity absorption	<b>1.5 / -</b>	%	Sim. to ISO 62
Density	<b>1310 / -</b>	kg/m <sup>3</sup>	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	<b>0.1 / -</b>	%	ISO 294-4, 2577
Molding shrinkage (normal)	<b>0.2 / -</b>	%	ISO 294-4, 2577


**Diagrams**

**Grilon TSC-40/4 EC black 9832**


PA666-CF40

EMS-GRIVORY | a unit of EMS-CHEMIE AG


**Dynamic Shear modulus-temperature**



**Dynamic Shear modulus-temperature**



**Specific volume-temperature (pvT)**



**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Granules

**Special Characteristics**

Anti-static

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Chemical Media Resistance**

**Acids**

**Product Attributes**

Improved friction & wear properties

**Automotive**

Automotive electr. and electronics, lighting, Powertrain and Chassis

**Electricals & Electronics**

Electrical appliances, Electrical equipment









**Industry & Consumer goods**

Mechanical Engineering, Power transmission, Sports & Leisure, Tools & Accessories




**Grilon TSC-40/4 EC black 9832**

PA666-CF40




EMS-GRIVORY | a unit of EMS-CHEMIE AG

-  Acetic Acid (5% by mass) (23°C)
-  Citric Acid solution (10% by mass) (23°C)
-  Lactic Acid (10% by mass) (23°C)
-  Hydrochloric Acid (36% by mass) (23°C)
-  Nitric Acid (40% by mass) (23°C)
-  Sulfuric Acid (38% by mass) (23°C)
-  Sulfuric Acid (5% by mass) (23°C)
-  Chromic Acid solution (40% by mass) (23°C)




**Bases**

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

**Alcohols**

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)


**Hydrocarbons**

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)





**Ketones**

-  Acetone (23°C)










**Ethers**

-  Diethyl ether (23°C)

**Mineral oils**

-  SAE 10W40 multigrade motor oil (23°C)
-  SAE 10W40 multigrade motor oil (130°C)
-  SAE 80/90 hypoid-gear oil (130°C)
-  Insulating Oil (23°C)

**Standard Fuels**

-  ISO 1817 Liquid 1 (60°C)
-  ISO 1817 Liquid 2 (60°C)
-  ISO 1817 Liquid 3 (60°C)
-  ISO 1817 Liquid 4 (60°C)
-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
-  Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)





**Salt solutions**

-  Sodium Chloride solution (10% by mass) (23°C)










Grilon TSC-40/4 EC black 9832

PA666-CF40

EMS-GRIVORY | a unit of EMS-CHEMIE AG

-  Sodium Hypochlorite solution (10% by mass) (23°C)
-  Sodium Carbonate solution (20% by mass) (23°C)
-  Sodium Carbonate solution (2% by mass) (23°C)
-  Zinc Chloride solution (50% by mass) (23°C)

Other

-  Ethyl Acetate (23°C)
  -  Hydrogen peroxide (23°C)
  -  DOT No. 4 Brake fluid (130°C)
  -  Ethylene Glycol (50% by mass) in water (108°C)
  -  1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
  -  50% Oleic acid + 50% Olive Oil (23°C)
  -  Water (23°C)
  -  Deionized water (90°C)
  -  Phenol solution (5% by mass) (23°C)
-