

**Grivory HT2VZ-33H**

PA6T/66-GF33

EMS-GRIVORY | a unit of EMS-CHEMIE AG

**Product Texts**

Product designation according to ISO 1874:

PA 6T/66, MH, 14-110, GF33

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	<b>11000 / 11000</b>	MPa	ISO 527-1/-2
Stress at break	<b>200 / 180</b>	MPa	ISO 527-1/-2
Strain at break	<b>2.5 / 2.5</b>	%	ISO 527-1/-2
Charpy impact strength (+23°C)	<b>55 / 55</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	<b>50 / 45</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	<b>10 / 10</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	<b>9 / 9</b>	kJ/m <sup>2</sup>	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	<b>260 / 240</b>	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	<b>310 / -</b>	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	<b>285 / -</b>	°C	ISO 75-1/-2
Temp. of deflection under load (8.00 MPa)	<b>200 / -</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	<b>20 / -</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	<b>60 / -</b>	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	<b>HB / -</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / -</b>	mm	IEC 60695-11-10
Max. usage temperature (long term)	<b>140</b>	°C	ISO 2578
Max. usage temperature (short term)	<b>260</b>	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	<b>1E10 / 1E10</b>	Ohm*m	IEC 60093
Surface resistivity	<b>- / 1E12</b>	Ohm	IEC 60093
Electric strength	<b>38 / 37</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>- / 600</b>	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	<b>5 / -</b>	%	Sim. to ISO 62
Humidity absorption	<b>2 / -</b>	%	Sim. to ISO 62
Density	<b>1440 / -</b>	kg/m <sup>3</sup>	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	<b>0.1 / -</b>	%	ISO 294-4, 2577
Molding shrinkage (normal)	<b>0.9 / -</b>	%	ISO 294-4, 2577

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Granules

**Automotive**

Automotive electr. and electronics, lighting, Fuel systems, Powertrain and Chassis , Interior, Exterior

**Electricals & Electronics**

Electrical equipment, Connectors

## Grivory HT2VZ-33H

PA6T/66-GF33

EMS-GRIVORY | a unit of EMS-CHEMIE AG

### Special Characteristics

High impact or impact modified, Improved UV resistance (outdoor use), Improved heat resistance

### Industry & Consumer goods

Housewares, Hydraulics & Pneumatics, Mechanical Engineering, Power transmission, Sports & Leisure, Tools & Accessories

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

---