

# AF312B

## Description

AF312B is an ABS product apply for injection molding, with 2.1mm V-0 flame retardancy and high flow

## Key Features

Opacity, Flame Retardancy, Hot Stamping, Paintability, High Gloss, Dimensional Stability, High Flow

## Application

Heater, electric control box, Charge bank, hair dryer

## Plant

China(Huizhou)

Properties	Condition	Method	Unit	AF312B
<b>Physical</b>				
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	55
<b>Mechanical</b>				
Tensile Strength at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	MPa	42
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	60
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	2250
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	J/m	21
Rockwell Hardness	R-Scale	ASTM D785		100
<b>Thermal</b>				
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	74

## Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

# AF312B

## Description

AF312B is an ABS product apply for injection molding, with 2.1mm V-0 flame retardancy and high flow

## Key Features

Opaqueness, Flame Retardancy, Hot Stamping, Paintability, High Gloss, Dimensional Stability, High Flow

## Application

Heater, electric control box, Charge bank, hair dryer

## Plant

China(Huizhou)

## Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	70~80
Drying Time	hrs	2~4
Injection Temperature	°C	190~230
Mold Temperature	°C	40~70
Screw Speed	rpm	30~60

## Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.