

AF364

Description

AF364 is a Flame Retardant ABS product for injection molding and extrusion, designed to have a flammability rating of V-0 at 1.5mm and medium heat resistance.

Key Features

High Flame Retardancy, Medium Heat Resistance

Application

Hair Dryer, Terminal Box, Electrical/Electronic Products

Properties	Condition	Method	Unit	AF364
Physical				
Specific Gravity	23°C	ASTM D792		1.17
Mold Shrinkage	23°C, 3.2mm	ASTM D955	%	0.4 ~ 0.7
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	10
Mechanical				
Tensile Strength at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	MPa	44
Tensile Elongation at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	5
Tensile Elongation at Break	23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	15
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	74
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	2450
Izod Impact Strength	Notched, 3.2mm, 23°C	ASTM D256	J/m	180
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	J/m	150
Rockwell Hardness	R-Scale	ASTM D785		105
Thermal				
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	93
Vicat Softening Temperature	50N, 50°C/h	ASTM D1525	°C	100
Flammability	1.5mm	UL 94		V-0
Flammability	2.0mm	UL 94		V-0, 5VA
Flammability	3.0mm	UL 94		V-0, 5VA

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

AF364

Description

AF364 is a Flame Retardant ABS product for injection molding and extrusion, designed to have a flammability rating of V-0 at 1.5mm and medium heat resistance.

Key Features

High Flame Retardancy, Medium Heat Resistance

Application

Hair Dryer, Terminal Box, Electrical/Electronic Products

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	70 ~ 80
Drying Time	hrs	3 ~ 4
Injection Temperature	°C	200 ~ 240
Mold Temperature	°C	40 ~ 80
Screw Speed	rpm	30 ~ 60

Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.