

# AF365HB

## Description

AF365HB is an ABS product apply for injection molding, with 2.0mm V-0 flame retardancy, high Thermal resistance, good Thermal stability, and high impact

## Key Features

Opacity, Flame Retardancy, Medium Heat Resistance, Hot Stamping, Paintability, High Gloss, Bright White, Thermal Stability, Colorability, High Impact Strength

## Application

Special for battery

## Plant

China(Huizhou)

Properties	Condition	Method	Unit	AF365HB
<b>Physical</b>				
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	25
<b>Mechanical</b>				
Tensile Strength at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	MPa	41
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	61
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	MPa	2150
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	J/m	33
Rockwell Hardness	R-Scale	ASTM D785		100
<b>Thermal</b>				
Heat Deflection Temperature	Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	83

## Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

# AF365HB

## Description

AF365HB is an ABS product apply for injection molding, with 2.0mm V-0 flame retardancy, high Thermal resistance, good Thermal stability, and high impact

## Key Features

Opaqueness, Flame Retardancy, Medium Special for battery  
Heat Resistance, Hot Stamping,  
Paintability, High Gloss, Bright White,  
Thermal Stability, Colorability, High  
Impact Strength

## Application

## Plant

China(Huizhou)

## Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	80~90
Drying Time	hrs	3~4
Injection Temperature	°C	200~230
Mold Temperature	°C	40~60
Screw Speed	rpm	30~60

## Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.