

# LI952

## Description

LI952 has low VOC content and gloss ASA with weatherability, targeted for interior parts

## Key Features

High Heat Resistance, Non Painting, Low TVOC,  
Weatherability, Low Gloss

## Application

Cockpit,Door Trim,Interior ETC

Properties	Condition	Method	Unit	LI952
<b>Optical</b>				
Haze		ASTM D1003	%	2.3
Luminous Transmittance	3.2mm	ASTM D1003	%	90

## Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors. Values given should not be interpreted as specification and not be used for designing part or tool. All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

# LI952

## Description

LI952 has low VOC content and gloss ASA with weatherability, targeted for interior parts

## Key Features

High Heat Resistance, Non Painting, Low TVOC,  
Weatherability, Low Gloss

## Application

Cockpit,Door Trim,Interior ETC

## Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	80 ~ 90
Drying Time	hrs	3 ~ 4
Injection Temperature	°C	220 ~ 270
Mold Temperature	°C	40 ~ 80
Screw Speed	rpm	30 ~ 60

## Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.