

LF2003N

Description

High mechanical properties for shrinkage film
Additives : Non-Slip & Non-Antiblock agent

Application

shrinkage film, cutting board

Properties	Method	Condition	Unit	LF2003N
Physical				
MFI	ASTM D1238	190°C, 2.16kg load	g/10min	0.8
Density	ASTM D1505	Density-Gradient	g/cm ³	0.921
Film Properties				
Tensile Strength at Break Point, MD	ASTM D882	500mm/min	kgf/cm ²	290
Tensile Strength at Break Point, TD	ASTM D882	500mm/min	kgf/cm ²	270
Elongation at Break Point, MD	ASTM D882	500mm/min	%	280
Elongation at Break Point, TD	ASTM D882	500mm/min	%	580
Dart Impact Strength	ASTM D1709	Method A	g	340
Haze(55μm)	ASTM D1003	55μm	%	18
Thermal				
Melting Temperature	LG Method	by DSC	°C	110
Vicat Softening Temperature	ASTM D1525	A50	°C	94

Note

The properties data in this table are typical values, and not guaranteed specification.
Typical resin property values are measured on film specimens.