

# NBR 2860

## Description

Excellent physical properties and good elasticity in low temperature  
 Non staining, medium mooney viscosity  
 Designed to aid in extruding, press molding

## Application

Hose, Belt

## Key Features

28 AN, Mid MV

Properties	Condition	Unit	NBR 2860	Method
<b>Polymer Property</b>				
Appearance			Light Tan	
Volatile Material		wt %	0.3	ASTM D5668
Ash		wt %	Max 1.0	ASTM D5667
Bound Acrylonitrile		%	28	LSD-R0-OP-6058
Polymer Viscosity	ML1+4, 100°C	MU	60	ASTM D1646
<b>Mechanical Property</b>				
Elongation		%	510	ASTM D412
300% Modulus		kg/cm <sup>2</sup>	120	ASTM D412

## Precaution

It should be stored in warehouse to be protected from sunlight, heat and moisture.

Shelf life : 18 month from date of production at room temperatures not exceeding 30°C under above storage condition (Retest critical parameters like MV and others after the expiry of shelf life)

## Package

35kg bale, 35kg X 36bales = 1.26MT box