

NBR 6280

Description

Excellent physical properties and sticky characteristic
 Non staining, high mooney viscosity
 Designed to aid in extruding, injection, and calendering

Application

Shoe Sole, Hose, Belt

Key Features

34 AN, High MV

Properties	Condition	Unit	NBR 6280	Method
Polymer Property				
Appearance			Light Tan	
Volatile Material		wt %	0.2	ASTM D5668
Ash		wt %	Max 0.5	ASTM D5667
Bound Acrylonitrile		%	34	LSD-R0-OP-6058
Polymer Viscosity	ML1+4, 100°C	MU	80	ASTM D1646
Mechanical Property				
Elongation		%	510	ASTM D412

Precaution

It should be stored in warehouse to be protected from sunlight, heat and moisture.

Shelf life : 18 month from date of production at room temperatures not exceeding 30°C under above storage condition (Retest critical parameters like MV and others after the expiry of shelf life)

Package

35kg bale, 35kg X 36bales = 1.26MT box