

RAW C9S

Description

Raw material of C9 Resin

Application

Raw Material of Resin

Properties	Method	Unit	RAW C9S
Actives	Gas Chro	wt %	> 45.0
Appearance	Visual		Clear
Benzene	Gas Chro	wt %	< 0.10
Color	SD DC-139	Gardner No	< 12
DCPD	Gas Chro	wt %	< 2.0
Naphthalene	Gas Chro	wt %	< 20.0
S/I Ratio**	Gas Chro		0.9~1.35
Sulfur	ASTM D-5453	wt ppm	< 360
TBC	ASTM D-1157	wt ppm	50~150
Water	ASTM D-1364	wt ppm	No Free Water