

M1425

Description

Polypropylene block copolymer for injection molding
 Excellent stiffness and good impact resistance
 Complies with FDA Regulations 21 CFR 177.1520 for food contact

Application

Outdoor Chairs, Industrial Parts

Properties	Method	Condition	Unit	M1425
Physical				
MFI	ASTM D1238	230°C, 2.16kg load	g/10min	10
Density	ASTM D1505	Density-Gradient	g/cm ³	0.9
Mechanical				
Tensile Strength at yield point(kgf/cm ²)	ASTM D638	50mm/min	kgf/cm ²	260
Elongation at Break Point	ASTM D638	50mm/min	%	<100
Flexural Modulus(kgf/cm ²)	ASTM D790	Press sheet, 1% Secant	kgf/cm ²	16500
Izod Impact Strength(kgf·cm/cm)	ASTM D256	23°C, Notched	kgf·cm/cm	10
Izod Impact Strength(kgf·cm/cm)	ASTM D256	-20°C, Notched	kgf·cm/cm	4
Rockwell Hardness(R-Scale)	ASTM D785	R-Scale		95
Thermal				
Vicat Softening Temperature	ASTM D1525	A50	°C	151
Heat Deflection Temperature	ASTM D648	4.6kgf/cm ²	°C	120

Note

The properties data in this table are typical values, and not guaranteed specification.
 Typical resin property values are measured on a standard injection molded specimens.