

SAN 81HF

Description

81HF is a SAN product for injection molding with high transparency, super high flow and balanced mechanical properties

Key Features

Transparency, Ultra High Flow

Application

glass fiber modified PC/ABS
modified

Plant

China(Ningbo)

Properties	Condition	Method	Unit	81HF China(Ningbo)
Physical				
Melt Flow Index	220°C, 10kg	ASTM D1238	g/10min	62
Mechanical				
Tensile Strength at Yield	23°C, 50mm/min, 3.2mm	ASTM D638	kg/cm ²	68
Flexural Strength	23°C, 10mm/min, 6.4mm	ASTM D790	kg/cm ²	115
Flexural Modulus	23°C, 10mm/min, 6.4mm	ASTM D790	kg/cm ²	3700
Izod Impact Strength	Notched, 6.4mm, 23°C	ASTM D256	kg-cm/cm	1.2
Rockwell Hardness	R-Scale	ASTM D785		123
Thermal				
Heat Deflection Temperature	Edgewise, 18.6kg, 6.4mm, Unannealed	ASTM D648	°C	90

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors.

Values given should not be interpreted as specification and not be used for designing part or tool.

All properties, except melt flow index are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

SAN 81HF

Description

81HF is a SAN product for injection molding with high transparency, super high flow and balanced mechanical properties

Key Features

Transparency, Ultra High Flow

Application

glass fiber modified PC/ABS
modified

Plant

China(Ningbo)

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	75~85
Drying Time	hrs	2~4
Injection Temperature	°C	180~220
Mold Temperature	°C	40~80
Screw Speed	rpm	30~60

Note

Injection Temperature & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.