

# F3626Y

## Description

Chain-end modified with functional group which give good compatibility with silica

## Application

Tire

## Key Features

High Oil, High Tg, Mid Molecular Weight, Processability, Traction (Grip)

Properties	Condition	Unit	F3626Y	Method
<b>Polymer Property</b>				
Appearance			Dark Brown	
Volatile Material		wt %	Max 0.75	ASTM D5668
Ash		wt %	Max 0.3	ASTM D5667
Bound Styrene		%	36.0±1.5	ASTM D5775
Vinyl Content		%	26.0±2.0	FT-IR
Oil Content (TDAE)		%	20.0±1.5	ASTM D5774
Polymer Viscosity (Massed)	ML1+4,100°C	MU	70±5	ASTM D1646

## Precaution

It should be stored in warehouse to be protected from sunlight, heat and moisture.

Shelf life : 18 month from date of production at room temperatures not exceeding 30°C under above storage condition (Retest critical parameters like MV and others after the expiry of shelf life)

## Package

35kg bale, 35kg X 30bales = 1.05MT box