



Sicostirolo® CR H 3441

Ravago Manufacturing Europe - High Impact Polystyrene

General Information

Product Description

High impact polystyrene, natural

General

Material Status	• Commercial: Active
Availability	• Europe
Features	• High Impact Resistance
Appearance	• Natural Color

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	7.0	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	20.0	MPa	ISO 527-2
Tensile Stress (Break)	16.0	MPa	ISO 527-2
Tensile Strain (Break)	30	%	ISO 527-2
Flexural Modulus	2000	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	7.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	70.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	82.0	°C	ISO 306/B50
--	90.0	°C	ISO 306/A50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength (1.00 mm, in Oil)	60	kV/mm	IEC 60243-1
Comparative Tracking Index	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.6 mm		HB	
3.2 mm		HB	
Glow Wire Flammability Index (2.0 mm)	550	°C	IEC 60695-2-12

Notes

¹ Typical properties: these are not to be construed as specifications.