



# Ravamid<sup>®</sup> B GB30 BK45

Polyamide 6  
Industrial Quality Compound

## Description:

Polyamide 6 black, containing recycled material, 30% glass beads reinforced, also available Heat Stabilized (H) and UV stabilized (UV)

## General

Density	ISO 1183	1.35	g/cm <sup>3</sup>
Mold shrinkage (Parallel)		1.00	%
Mold shrinkage (Perpendicular)		1.00	%

## Thermal

HDT/A (1,82MPa)	ISO 75A	80	°C
-----------------	---------	----	----

## Mechanical

Izod notched impact strength (23 °C)	ISO 180	6	kJ/m <sup>2</sup>
Charpy notched impact strength (23 °C)	ISO 179	6	kJ/m <sup>2</sup>
Charpy unnotched impact strength (23 °C)	ISO 179	30	kJ/m <sup>2</sup>
Tensile strength at yield (23 °C)	ISO 527	80	MPa
Tensile strength at break (23 °C)	ISO 527	75	MPa
Elongation at break (23 °C)	ISO 527	10	%
Flexural modulus (23 °C)	ISO 178	3500	MPa

## Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Burning rate (FMVSS 302)	ISO 3795	<100	mm/min
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

## Various

Humidity	ISO 960	≤0.15	%
----------	---------	-------	---