



Ravamid[®] B GF30 ST BK45

Polyamide 6
Industrial Quality Compound

Description:

Polyamide 6 black containing recycled material, 30% glass fiber reinforced, high impact modified, also available Heat Stabilized (H) and UV Stabilized (UV)

General

Density	ISO 1183	1.31	g/cm ³
Mold shrinkage (Parallel)		0.15	%
Mold shrinkage (Perpendicular)		0.70	%

Thermal

HDT/A (1,82MPa)	ISO 75A	175	°C
-----------------	---------	-----	----

Mechanical

Izod notched impact strength (23 °C)	ISO 180	12	kJ/m ²
Charpy notched impact strength (23 °C)	ISO 179	12	kJ/m ²
Charpy unnotched impact strength (23 °C)	ISO 179	65	kJ/m ²
Tensile strength at break (23 °C)	ISO 527	124	MPa
Elongation at break (23 °C)	ISO 527	5.0	%
Tensile modulus (23 °C)	ISO 527	7800	MPa
Flexural modulus (23 °C)	ISO 178	7000	MPa

Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Burning rate (FMVSS 302)	ISO 3795	<100	mm/min
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

Various

Humidity	ISO 960	<0.15	%
----------	---------	-------	---