

# Ravamid<sup>®</sup> B GF30 T BK45

Polyamide 6

Industrial Quality Compound

## Description:

Polyamide 6 containing recycled material, 30 % glass fibre reinforced, good mechanical properties, impact modified, also available UV Stabilized (UV)

## General

Density	ISO 1183	1.33	g/cm <sup>3</sup>
Mold shrinkage (Parallel)		0.20	%
Mold shrinkage (Perpendicular)		0.75	%

## Thermal

HDT/A (1,82MPa)	ISO 75A	188	°C
-----------------	---------	-----	----

## Mechanical

Izod notched impact strength (23 °C)	ISO 180	9	kJ/m <sup>2</sup>
Charpy notched impact strength (23 °C)	ISO 179	10	kJ/m <sup>2</sup>
Charpy unnotched impact strength (23 °C)	ISO 179	55	kJ/m <sup>2</sup>
Tensile strength at break (23 °C)	ISO 527	128	MPa
Elongation at break (23 °C)	ISO 527	4	%
Tensile modulus (23 °C)	ISO 527	8200	MPa
Flexural modulus (23 °C)	ISO 178	7500	MPa

## Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Burning rate (FMVSS 302)	ISO 3795	<100	mm/min
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

## Various

Humidity	ISO 960	<0.15	%
----------	---------	-------	---