



Ravamid® B GF50 BK45

Polyamide 6
Industrial Quality Compound

Description:

Polyamide 6 black containing recycled material, 50% glass fibre reinforced, good mechanical properties, also available Heat Stabilized (H) and UV Stabilized (UV)

General

Density	ISO 1183	1.56	g/cm ³
Mold shrinkage (Parallel)		0,20	%
Mold shrinkage (Perpendicular)		0,40	%

Thermal

HDT/A (1,82MPa)	ISO 75A	215	°C
-----------------	---------	-----	----

Mechanical

Izod notched impact strength (23°C)	ISO 180	11	kJ/m ²
Charpy notched impact strength (23 °C)	ISO 179	9	kJ/m ²
Charpy unnotched impact strength (23 °C)	ISO 179	65	kJ/m ²
Tensile stress at break	ISO 527	175	MPa
Elongation at break	ISO 527	1,5	%
Tensile modulus	ISO 527	12500	MPa
Flex modulus	ISO 178	9800	MPa

Flammability

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	HB	
Burning rate (FMVSS 302)	ISO 3795	<100	mm/min
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	650	°C

Various

Humidity	ISO 960	≤0.10	%
----------	---------	-------	---