



Hylon N1000STHL NAT

Polyamide 66 Prime Compound

Product Description : Unfilled, High Impact Modified, Polyamide 66 Compound

Key Features : HYLON N1000STHL NAT is high heat stabilized and lubricated PA66 compound with good toughness and stiffness balance properties

Process Method : Injection moulding

Uses : Recommended for automotive applications

Revision Date : 01.01.2023

	Value	Unit	Standard
Physical			
Density	1,07	gr / cm3	ISO 1183 1-A
Mechanical			
Tensile Stress at Break	45	MPa	ISO 527-1
Yield Strength	50	MPa	ISO 527-1
Elongation at Break	>40	%	ISO 527-1
Tensile Modulus	2000	MPa	ISO 527-1
Izod Impact Strength (Notched) (23°C)	80 (PB)	kJ/m2	ISO 180/1A
Charpy Impact Strength (Notched)	85 (PB)	kJ/m2	ISO 179/1A
Flexural Modulus	1600	Mpa	ISO 178
Flexural Strength	65	Mpa	ISO 178
Izod Impact Strength (Unnotched)	NB	kJ/m2	ISO 180/1A
Charpy Impact Strength (Unnotched)	NB	kJ/m2	ISO 179/1U
Thermal			
HDT (1.8 Mpa)	50	°C	ISO 75A
Vicat Softening Point (120°C/10N)	60	°C	ISO 306
Flammability			
Flammability (1,6 mm)	HB	*	UL 94
Flammability (3,2 mm)	HB	*	UL 94
Flammability (0,8 mm)	HB	*	UL 94



Hylon N1000STHL NAT

Polyamide 66 Prime Compound

Aging

Water Absorption	0,80	%	Internal Method
------------------	------	---	-----------------

Drying Condition

Drying Time(hr)	2-4
-----------------	-----

Drying Temperature(°C)	90
------------------------	----

Molding Condition (°C)

1st Zone (hopper)(°C)	250-270
-----------------------	---------

2nd Zone(°C)	260-280
--------------	---------

3rd Zone(°C)	270-290
--------------	---------

Nozzle(°C)	270-290
------------	---------

Mold Temperature(°C)	80
----------------------	----

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

REMARK:
THIS TDS APPLIES FOR THE ID OF 270289