



**Hylon N1050H2L NT034**

**Polyamide 66 Prime Compound**

**Product Description :** 50% Glass Fibre Reinforced, Polyamide 66 Compound

**Key Features :** HYLON N1050H2L NT034 is heat stabilized PA66 compound with excellent strength and stiffness properties

**Process Method :** Injection moulding

**Uses :** Recommended for general applications and purposes

**Revision Date :** 01.01.2023

	Value	Unit	Standard
<b>Physical</b>			
Density	1,57	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
Tensile Stress at Break	230	MPa	ISO 527-1
Yield Strength	232	MPa	ISO 527-1
Elongation at Break	2,2	%	ISO 527-1
Tensile Modulus	16500	MPa	ISO 527-1
Izod Impact Strength (Notched) (23°C)	19	kJ/m2	ISO 180/1A
Charpy Impact Strength (Notched)	19	kJ/m2	ISO 179/1A
Flexural Modulus	13000	Mpa	ISO 178
Flexural Strength	320	Mpa	ISO 178
Izod Impact Strength (Unnotched)	85	kJ/m2	ISO 180/1A
Charpy Impact Strength (Unnotched)	95	kJ/m2	ISO 179/1A
<b>Thermal</b>			
HDT (1.8 Mpa)	245	°C	ISO 75A
<b>Flammability</b>			
Flammability (1,6 mm)	HB	*	UL 94

**Drying Condition**

Drying Time(hr) 2-4



**Hylon N1050H2L NT034**

**Polyamide 66 Prime Compound**

---

Drying Temperature(°C)	90
------------------------	----

---

**Molding Condition (°C)**

1st Zone (hopper)(°C)	265-275
-----------------------	---------

2nd Zone(°C)	275-285
--------------	---------

3rd Zone(°C)	285-295
--------------	---------

Nozzle(°C)	285-295
------------	---------

Mold Temperature(°C)	80
----------------------	----

---

**Important Notice;**

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.

Ex : AM180GR9J1000