



ENESTER EM 180-GR8-HR-900

ENESTER-E

Product Description : 45% Glass Fiber Reinforced, Hydrolysis Resistant, Black Color, Polybutylene Terephthalate Compound

Key Features : ENESTER EM-180-GR8-HR-900 is a hydrolysis stabilized according to JEDEC STANDARD No 22-A110 and heat stabilized PBT compound with good strength and stiffness properties

Process Method : Injection moulding

Uses : Recommended for general purpose & applications.

Revision Date : 01.01.2024

	Value	Unit	Standard
Physical			
Density	1,63	gr / cm3	ISO 1183 1-A
Mechanical			
Tensile Stress at Break	130	MPa	ISO 527-1
Elongation at Break	1,4	%	ISO 527-1
Tensile Modulus	13500	MPa	ISO 527-1
Izod Impact Strength (Notched) (23°C)	8	kJ/m2	ISO 180/1A
Flexural Modulus	10500	Mpa	ISO 178
Flexural Strength	175	Mpa	ISO 178
Thermal			
Ash Content (600 °C)	45	%	ISO 3451-1

Drying Condition

Drying Time(hr) 2-4
 Drying Temperature(°C) 120-140

Molding Condition (°C)

1st Zone (hopper)(°C) 230-245
 2nd Zone(°C) 235-250
 3rd Zone(°C) 240-260



ENESTER EM 180-GR8-HR-900

ENESTER-E

Nozzle(°C)	240-260
Mold Temperature(°C)	40-80

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.