



	Sicoklar <sup>®</sup> Eco UG10 FV	
Polycarbonate		
Recycled Quality Compound		

**Description:**

PC, 10% glass fibre filled, recycled quality ISO 14021:2016 compliant

**General**

MFI (300°C/1,2kg)	ISO 1133	11	g/10min
Density	ISO 1183	1.25	g/cm <sup>3</sup>

**Thermal**

HDT/A (1,82MPa)	ISO 75A	135	°C
Vicat softening point (B50 (50N))	ISO 306	140	°C
Vicat softening point (A50(10N))	ISO 306	145	°C
Ball pressure test (125°C)	IEC 60695-10-2	Pass	°C

**Mechanical**

Izod notched impact strength (23°C)	ISO 180	8	kJ/m <sup>2</sup>
Izod notched impact strength (-30°C)	ISO 180	6	kJ/m <sup>2</sup>
Tensile stress at break	ISO 527	50	MPa
Elongation at break	ISO 527	5	%
Flex modulus	ISO 178	3200	MPa

**Flammability**

Flammability (3,2mm)	UL94	HB	
Flammability (1,6mm)	UL94	V2	
Flammability (0,75mm)	UL94	V2	
Glow wire flammability index (2,0 mm)	IEC 60695-2-12	850	°C

**Various**

Linear Mould Shrinkage	internal method	0.2-0.5	%
------------------------	-----------------	---------	---