



# Mablex® 466F

## Ravago Manufacturing Europe - Polycarbonate + ABS

### General Information

#### Product Description

PC/ABS blend high heat resistance grade, high gloss, improved flowability

#### General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Features	• Good Flow	• High Gloss	• High Heat Resistance

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	24	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	62.0	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	55.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	50	%	ISO 527-2
Flexural Modulus (23°C)	2300	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/A
-30°C	30	kJ/m <sup>2</sup>	
23°C	55	kJ/m <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	113	°C	ISO 75-2/A
Vicat Softening Temperature			
--	128	°C	ISO 306/B50
--	138	°C	ISO 306/A120
Ball Pressure Test (125°C)	Pass		
Flammability	Nominal Value	Unit	Test Method
Burning Rate <sup>2</sup>	24	mm/min	ISO 3795
Flame Rating			UL 94
1.6 mm	HB		
3.2 mm	HB		
Glow Wire Flammability Index (2.0 mm)	750	°C	IEC 60695-2-12

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> FMVSS 302