



# Mablex® 478E

## Ravago Manufacturing Europe - Polycarbonate + ABS

### General Information

General			
Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Features	• Antimony Free • Bromine Free	• Chlorine Free • Flame Retardant	• Good Thermal Stability • Non-Blooming
Processing Method	• Extrusion		

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	10	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 0.70	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	50.0	MPa	ISO 527-2
Tensile Stress (Break)	45.0	MPa	ISO 527-2
Tensile Strain (Break)	45	%	ISO 527-2
Flexural Modulus	2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180
-30°C	25	kJ/m <sup>2</sup>	
23°C	50	kJ/m <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	94.0	°C	ISO 75-2/A
Vicat Softening Temperature	112	°C	ISO 306/B50
Thermal Conductivity	0.20	W/m/K	ISO 8302
Ball Pressure Test (75°C)	Pass		
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength (1.00 mm, in Oil)	30	kV/mm	IEC 60243-1
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.6 mm	V-0		
3.2 mm	V-0		
Glow Wire Flammability Index (2.0 mm)	960	°C	IEC 60695-2-12

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.