



# Mablex® Eco PCX

## Ravago Manufacturing Europe - Polycarbonate + ABS

### General Information

#### Product Description

PC/ABS blend general purpose grade, recycled quality ISO 14021:2016 compliant, only available in black color.

#### General

Material Status	• Commercial: Active
Availability	• Europe • North America
Recycled Content	• Yes
Features	• General Purpose
Uses	• General Purpose
Agency Ratings	• ISO 14021 :2016
Appearance	• Black

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	30	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 0.70	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	45.0	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	35.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	28	%	ISO 527-2
Flexural Modulus (23°C)	2300	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	25	kJ/m <sup>2</sup>	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	108	°C	ISO 75-2/A
Vicat Softening Temperature			
--	120	°C	ISO 306/B50
--	126	°C	ISO 306/A50
Ball Pressure Test (75°C)	Pass		
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.6 mm	HB		
3.2 mm	HB		
Glow Wire Flammability Index (2.0 mm)	650	°C	IEC 60695-2-12

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.