



# Aurapene® PPUFBK55

## OVERVIEW

Description	General purpose polypropylene compound manufactured from recycled polymer
Visual	Black

## GENERAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
Melt flow index (230°C / 2.16 kg)	50 – 60	g/10 min	ISO 1133
Specific gravity	0.904	g/cm <sup>3</sup>	ISO R 1183
Moisture	0.01	%	In house

## MECHANICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
Izod notched impact (23°C)	4	kJ/m <sup>2</sup>	ISO 180

**Note:** Properties not to be construed as specifications