



Mafill® CR XM 6546 K00C

Polypropylene
Industrial Quality Compound

Description:

PP compound, 30% mineral filled, white

General

MFI (230°/2,16kg)	ISO 1133	20	g/10min
Density	ISO 1183	1.14	g/cm ³

Mechanical

Izod notched impact strength (23 °C)	ISO 180	6	kJ/m ²
Flexural modulus (23 °C)	ISO 178	1500	MPa

Flammability

Flammability (1,6mm)	UL94 (tested internally)	HB
Flammability (3,2mm)	UL94 (tested internally)	HB

Various

Ash content (600 °C)	ISO 3451	30	%
----------------------	----------	----	---