



## RAVAPURA® PP 3001

Polypropylene compound with 30% post-consumer recycled content

### OVERVIEW

<b>Description</b>	PP compound based on post-consumer recycled (PCR) material
<b>Applications</b>	Extrusion
<b>Filler type &amp; content</b>	Unfilled
<b>% of total recycled content on compound</b>	30% PCR
<b>Certification</b>	Declaration available upon request
<b>Visual</b>	Black

### GENERAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
<b>MFI (230°C / 2.16 kg)</b>	0.5	g/10 min	ISO 1133
<b>Ash content (600°C)</b>	2	%	ISO 3451

### MECHANICAL PROPERTIES

	Nominal Value (SI)	Unit	Test Method
<b>Charpy notched impact strength (23°C)</b>	35	kJ/m <sup>2</sup>	ISO 179
<b>Charpy unnotched impact strength (23°C)</b>	NB	kJ/m <sup>2</sup>	ISO 179
<b>Tensile Modulus (23°C)</b>	1150	MPa	ISO 527

**Note:** Preliminary datasheet

Properties not to be construed as specifications