



■ Scolefin[®] 22 T 14-9

Polypropylene
Prime Compound

Description:

PPH, 20% mineral filled, long term heat stabilized, black

General

MFI (230°/2,16kg)	ISO 1133	3	g/10min
Density	ISO 1183	1.07	g/cm ³

Mechanical

Charpy notched impact strength (23 °C)	ISO 179	5	kJ/m ²
Charpy unnotched impact strength (23 °C)	ISO 179	54	kJ/m ²
Tensile strength at yield (23 °C)	ISO 527	30	MPa
Tensile modulus (23 °C)	ISO 527	3000	MPa
Flexural modulus (23 °C)	ISO 178	2600	MPa

Various

Ash content (600 °C)	ISO 3451	20	%
----------------------	----------	----	---