



# ■ Scolefin<sup>®</sup> 52 T 10-0

Polypropylene  
Prime Compound

**Description:**

PPH, 20% mineral filled, natural

**General**

MFI (230°/2,16kg)	ISO 1133	11	g/10min
Density	ISO 1183	1.05	g/cm <sup>3</sup>

**Thermal**

HDT/A (1,82MPa)	ISO 75A	60	°C
-----------------	---------	----	----

**Mechanical**

Charpy notched impact strength (23 °C)	ISO 179/1eA	3	kJ/m <sup>2</sup>
Charpy unnotched impact strength (23 °C)	ISO 179/1eU	40	kJ/m <sup>2</sup>
Tensile stress at yield	ISO 527	32	MPa
Tensile modulus	ISO 527	2800	MPa

**Various**

Ash content (700 °C)	ISO 3451	20	%
----------------------	----------	----	---