



# Scolefin® 53 G 13-9

## Ravago Manufacturing Europe - Polypropylene Homopolymer

### General Information

#### Product Description

PPH, 30% glass filled, chemically coupled, long term heat stabilized, black, available in different colours

#### General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Chemically Coupled	• Heat Stabilized	
Appearance	• Black	• Colors Available	

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.20	%	
Molding Shrinkage - Across Flow	0.80	%	
Ash Content (625°C)	30	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	6500	MPa	ISO 527-1
Tensile Stress (Yield, 23°C)	85.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	5.0	%	ISO 527-2
Flexural Modulus (23°C)	6700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10	kJ/m <sup>2</sup>	ISO 179
Charpy Unnotched Impact Strength (23°C)	45	kJ/m <sup>2</sup>	ISO 179
Notched Izod Impact Strength (23°C)	10	kJ/m <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	150	°C	ISO 75-2/A
Vicat Softening Temperature	135	°C	ISO 306/B50

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.