



Scolefin® 61 M 23

Ravago Manufacturing Europe - Polypropylene

General Information

Product Description

PP Prime compound, light weight, aesthetical surface, excellent balance impact-stiffness, scratch resistant, for interior automotive trims, coloured on request

General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Features	• Good Impact Resistance • Good Scratch Resistance	• Good Stiffness • Pleasing Surface Appearance
Uses	• Automotive Interior Trim	
Appearance	• Colors Available	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.980	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Ash Content (600°C)	10	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1450	MPa	ISO 527-1
Tensile Stress (Yield)	17.0	MPa	ISO 527-2
Tensile Stress (Break)	12.0	MPa	ISO 527-2
Tensile Strain (Break)	48	%	ISO 527-2
Flexural Modulus	1600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	25	kJ/m ²	ISO 180

Notes

¹ Typical properties: these are not to be construed as specifications.