



# Scolefin® 61 M 24

## Ravago Manufacturing Europe - Polypropylene

### General Information

#### Product Description

PP/EPR blend, 10% mineral filled, impact modified, scratch resistance

#### General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Filler / Reinforcement	• Mineral, 10% Filler by Weight		
Additive	• Rubber Impact Modifier		
Features	• Good Scratch Resistance	• Impact Modified	

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	0.980	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	13	g/10 min	ISO 1133
Ash Content (600°C)	10	%	ISO 3451
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2300	MPa	ISO 527-1
Tensile Stress (Yield)	24.0	MPa	ISO 527-2
Tensile Strain (Yield)	4.0	%	ISO 527-2
Tensile Strain (Break)	10	%	ISO 527-2
Flexural Modulus	2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	24	kJ/m <sup>2</sup>	ISO 180

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.