



# Scolefin® 62 T 20-0

## Ravago Manufacturing Europe - Polypropylene Copolymer

### General Information

#### Product Description

PP Copolymer, 20% talc filled improved flowability

#### General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Filler / Reinforcement	• Talc, 20% Filler by Weight	
Features	• Copolymer	• Good Flow

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-1
Tensile Stress	25.0	MPa	ISO 527-2
Tensile Strain (Break)	24	%	ISO 527-2
Flexural Modulus	2100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	5.0	kJ/m <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 0.45 MPa, Unannealed	115	°C	ISO 75-2/B

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.