



RAVATHANE

Technical Data Sheet

R130D70

Description: Product is based on standard grade saturated polyester and has strong resilience and tear resistance, excellent abrasion resistance, higher resistance to hydrolysis failure and oxidation, good stability towards solvents and light.

Application: Injection part, heel, shoes etc.

Typical Properties

PROPERTIES	METHOD	UNITS (English Metric)	NOMINAL VALUES
Hardness	DIN 53505 – ISO 868	Shore A	70D
Density	DIN ISO 1183 – 1 A	g/cm ³	1,23
100% modulus	DIN 53504 – ISO 37	MPa	25
300% modulus	DIN 53504 – ISO 37	MPa	36
Tensile strength	DIN 53504 – ISO 37	MPa	50
Elongation at break	DIN 53504 – ISO 37	%	440
Tear strength	DIN ISO 34 – 1 B/b	N/mm	260
Abrasion Resistance	DIN ISO 4649	mm ³	40

Application Guideline (Injection Molding)

Nozzle (°C)	Metering (°C)	Compression (°C)	Feed (°C)	Pressure (Mpa)	Drying Temp. (°C)
225	220	215	210	75	100-110



Manufacturer : RAVAGO KİMYA Plastik San. ve Tic. A.Ş.



Supplier : ENPLAST Plastik Kimya San. ve Tic. A.Ş.