



ENSOFT SD-141-75A

ENSOFT-S

Product Description : This polyolefin based thermoplastic elastomer (SEBS) compound is medium mineral filled, completely recyclable and suitable for general purpose applications. ENSOFT® series can be processed with conventional thermoplastics machinery

Additive Packages : D / Heat and UV stabilizer and lubricant /

Key Features : Excellent ozone, UV and weathering resistance
Rubberlike elasticity in a wide temperature range
Easy colorability with proper MB (PE, PP, etc. Based)

Process Method : Extrusion, coextrusion, sheet extrusion

Uses : Extruded parts (seals, tubes, profiles, hoses, etc.) for automotive, construction, home appliances, furniture

	Value	Unit	Standard
Physical			
Hardness	75	SHORE A	ISO 868 (3 second)
Density	1,08	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	2,6	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	3,7	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	11,8	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	640	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	39	N/mm	ISO 34-1 Method B
Aging			
Compression Set (72h/23°C)	28	%	ISO 815
Compression Set (22h/70°C)	47	%	ISO 815

Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair



Ravago Petrokimya Uretim A.S.



ENSOFT SD-141-75A

ENSOFT-S

Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

