



**ENSOFT SD-300-55A**

**ENSOFT-S**

**Product Description :** This polyolefin based thermoplastic elastomer (SEBS) compound is unfilled, high performance and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery

**Additive Packages :** T / Heat and UV stabilizer  
/

**Key Features :** Translucent  
Excellent ozone, UV and weathering resistance  
Rubberlike elasticity in a wide temperature range  
Low compression set  
Easy colorability with proper MB (PE, PP, etc. based)

**Process Method :** Extrusion, coextrusion, sheet extrusion

**Uses :** Extruded parts (seals, tubes, profiles, hoses, etc.) for construction, furniture, home appliances

	Value	Unit	Standard
<b>Physical</b>			
Hardness	55	SHORE A	ISO 868 (3 second)
Density	0,89	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	1,4	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	2,2	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	10	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	700	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	32	N/mm	ISO 34-1 Method B
<b>Aging</b>			
Compression Set (72h/23°C)	19	%	ISO 815
Compression Set (22h/70°C)	41	%	ISO 815
<b>Environmental Resistance</b>			
Ozone	Excellent		
Water	Excellent		



Ravago Petrokimya Uretim A.S.



## ENSOFT SD-300-55A

### ENSOFT-S

---

Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

---

#### Drying Condition

Drying Time(hr)	Not required
Drying Temperature(C)	Not required

---

#### Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

#### Important Notice;

---

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.