



ENSOFT SD-654-60A

ENSOFT-S

Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(C)	Not required

Extrusion Condition (°C)

Feed Zone Temperature (°C)	150 - 170
Compression Zone Temperature (°C)	160 - 175
Melting Zone Temperature (°C)	170 - 180
Extruder Head Temperature (°C)	180 - 190
Die Temperature (°C)	180 - 200

