



ENSOFT SD-661-90A

ENSOFT-S

Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is standard, high mineral filled SEBS series, completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery.
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Rubberlike elasticity Ease of coloring by proper MB (PE,PP,etc. based) Medium compression set Ease of processing Recyclability
Process Method :	Extrusion, coextrusion, sheet extrusion
Uses :	Extruded parts(seals, tubes, profiles, hoses, etc.) for automotive, construction, home appliances, furniture

	Value	Unit	Standard
Physical			
Hardness	90	SHORE A	ISO 868 (3 second)
Density	1,18	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	4,7	Mpa	ISO 37, DIN 53504
300% Modulus	5,8	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	8,7	Mpa	ISO 37, DIN 53504
Elongation at Break	550	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	62	kN/m	ISO 34-1
Aging			
Compression Set (72h/23°C)	44	%	ISO 815
Compression Set (22h/70°C)	67	%	ISO 815

Environmental Resistance

Ozone	Excellent
Water	Excellent



Ravago Petrokimya



ENSOFT SD-661-90A

ENSOFT-S

Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Molding Condition (°C)

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

