



ENSOFIT SL-300-80A

Ravago Manufacturing Turkey - Thermoplastic Elastomer

General Information

General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Features	• Ozone Resistant	• UV Resistant
Appearance	• Clear/Transparent	
Processing Method	• Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	2.90	MPa	ISO 37
Tensile Stress (300% Strain)	3.90	MPa	ISO 37
Tensile Stress (Break)	11.0	MPa	ISO 37
Tensile Elongation (Break)	700	%	ISO 37
Compression Set			ASTM D395B
23°C, 22 hr	25	%	
70°C, 22 hr	54	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	80		ISO 868

Additional Information

The value listed as Density, ISO 1183, was tested in accordance with ISO 2781.
 Tear Strength, ISO 34-2: 38 kN/m
 Tensile Strain at Break, ISO 37: >700%
 Ozone Resistance, ISO 1431: No Crack

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	150 to 160	°C
Front Temperature	170 to 180	°C
Nozzle Temperature	185 to 190	°C
Processing (Melt) Temp	190 to 200	°C
Mold Temperature	10 to 50	°C
Screw L/D Ratio	20.0:1.0	
Screw Compression Ratio	2.5:1.0	

Notes

¹ Typical properties: these are not to be construed as specifications.