



Preliminary ENSOFT SL66085A

ENSOFT

Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is high mineral filled, completely recyclable and suitable for general purpose applications. ENSOFT® series can be processed with conventional thermoplastics machinery.
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Good ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. based)
Process Method :	Extrusion, coextrusion, sheet extrusion
Uses :	Extruded parts (seals, tubes, profiles, hoses, etc.) for automotive, construction, home appliances, furniture

	Value	Unit	Standard
Physical			
Hardness	85	SHORE A	ISO 868 (3 second)
Density	1,17	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	2,6	Mpa	ISO 37, DIN 53504
300% Modulus	3,3	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	10	Mpa	ISO 37, DIN 53504,ASTM D412
Elongation at Break	700	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	40	N/mm	ISO 34-1

Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good



Ravago Petrokimya Uretim A.S.



Preliminary ENSOFT SL66085A

ENSOFT

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required
Max Allowable Melt Temperature(°C)	250 C

Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

