



**Preliminary SO-400-80A**

**ENSOF-T-S**

**Product Description :** This polyolefin based thermoplastic elastomer (SEBS) compound is transparent, unfilled and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery

**Additive Packages :** T / Heat and UV stabilizer  
/

**Key Features :** Transparent  
Weathering resistance  
Rubberlike elasticity in a wide temperature range  
Easy colorability with proper MB (PE, PP, etc. based).

**Process Method :** Injection/multi injection molding

**Uses :** Industrial applications, personal care, toys, consumer goods

	Value	Unit	Standard
<b>Physical</b>			
Hardness	80	SHORE A	ISO 868 (3 second)
Density	0,9	gr / cm3	ISO 1183 1-A
Brittleness Temperature	-55	°C	ASTM D746
<b>Mechanical</b>			
100% Modulus	4,1	Mpa	ISO 37, DIN 53504
300% Modulus	5,1	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	7,3	Mpa	ISO 37, DIN 53504
Elongation at Break	600	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	41	N/mm	ISO 34-1
<b>Thermal</b>			
Max. Dynamic Service Temperature	90	°C	*
Max. Static Service Temperature	135	°C	*
<b>Environmental Resistance</b>			
Ozone	Excellent		
Water	Excellent		



Ravago Petrokimya Uretim A.S.



## Preliminary SO-400-80A

### ENSOFT-S

---

Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

#### Drying Condition

---

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

#### Molding Condition (°C)

---

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

