



ENSOFT SX-141-30A

Ravago Manufacturing Turkey - 塑性 性体

一般信息

品 明

This polyolefin based thermoplastic elastomer (SEBS) compound is medium mineral filled, completely recyclable and suitable for general purpose applications. ENSOFT® series can be processed with conventional thermoplastics machinery

Additive Packages :

T / Heat and UV stabilizer

Key Features :

Excellent ozone, UV and weathering resistance

Rubberlike elasticity in a wide temperature range

Super high flow for difficult injection molding applications

Easy colorability with proper MB (PE, PP, etc. based)

Process Method :

Injection/multi injection molding

Uses :

Industrial applications, automotive, personal care, toys, consumer goods, home&kitchen appliances

材料状 <input type="checkbox"/>	• 已商用: 当前有效		
供 <input type="checkbox"/> 地区	• 北美洲	• 欧洲	
填料/增 <input type="checkbox"/> 材料	• <input type="checkbox"/> 物填料		
添加 <input type="checkbox"/>	• <input type="checkbox"/> <input type="checkbox"/> 定 <input type="checkbox"/>	• 紫外 <input type="checkbox"/> <input type="checkbox"/> 定 <input type="checkbox"/>	
特性	<ul style="list-style-type: none"> • 可回收材料 • 流 <input type="checkbox"/> 性高 • <input type="checkbox"/> <input type="checkbox"/> 定性 • 耐候性, 良好 	<ul style="list-style-type: none"> • 耐化学品性能, 良好 • 耐紫外光安定化 • 耐紫外光性能, 良好 • 耐臭氧性能 	<ul style="list-style-type: none"> • 良好的着色性 • 高 <input type="checkbox"/> 性
用途	<ul style="list-style-type: none"> • 个人 <input type="checkbox"/> 理 • 工 <input type="checkbox"/> <input type="checkbox"/> 用 	<ul style="list-style-type: none"> • 汽 <input type="checkbox"/> <input type="checkbox"/> 域的 <input type="checkbox"/> 用 • 消 <input type="checkbox"/> 品 <input type="checkbox"/> 用 <input type="checkbox"/> 域 	<ul style="list-style-type: none"> • 玩具 • <input type="checkbox"/> 器用具
加工方法	• 多次注射成型		
	• 注射成型		

属性¹

物理性能	<input type="checkbox"/> 定 <input type="checkbox"/> <input type="checkbox"/> 位制	<input type="checkbox"/> <input type="checkbox"/> 方法
密度	1.10 g/cm ³	ISO 1183/A
<input type="checkbox"/> 性体	<input type="checkbox"/> 定 <input type="checkbox"/> <input type="checkbox"/> 位制	<input type="checkbox"/> <input type="checkbox"/> 方法
拉伸 <input type="checkbox"/> 力 (100% <input type="checkbox"/> <input type="checkbox"/>)	0.400 MPa	ISO 37
拉伸 <input type="checkbox"/> 力 (300% <input type="checkbox"/> <input type="checkbox"/>)	0.800 MPa	ISO 37
拉伸 <input type="checkbox"/> 力 (断裂)	3.70 MPa	ISO 37
伸 <input type="checkbox"/> 率 (断裂)	800 %	ISO 37
撕裂 <input type="checkbox"/> 度 - 横向流量	16.0 kN/m	ISO 34-1
<input type="checkbox"/> <input type="checkbox"/> 永久 <input type="checkbox"/> 形		ASTM D395B
23°C, 72 hr	16 %	
70°C, 22 hr	32 %	

ENSOFIT SX-141-30A

Ravago Manufacturing Turkey - 塑性 性体

硬度	<input type="checkbox"/> 定 <input type="checkbox"/> 位制	<input type="checkbox"/> 方法
肖氏硬度 (邵氏 A, 3 秒)	30	ISO 868
<input type="checkbox"/> 性能	<input type="checkbox"/> 定 <input type="checkbox"/> 位制	
脆化温度	-55.0 °C	
Service Temperature		
Dynamic	90 °C	
Static	110 °C	

加工信息

注射	<input type="checkbox"/> 定 <input type="checkbox"/> 位制
料斗温度	170 到 180 °C
料筒中部温度	180 到 190 °C
料筒前部温度	190 到 200 °C
射嘴温度	200 到 210 °C
加工 (熔体) 温度	210 到 220 °C
模具温度	50 °C

注射 明

Max Allowable Melt Temperature: 250°C

注

¹ 一般属性: 些不能被 格。