



**ENSOFT SX-400-65A**

**ENSOFT-S**

**Product Description :** This polyolefin based thermoplastic elastomer (SEBS) compound is produced with food contact compliant raw materials, unfilled and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery

**Additive Packages :** T / Heat and UV stabilizer  
/

**Key Features :** Transparent  
Ozone and weathering resistance  
Rubberlike elasticity in a wide temperature range  
Super high flow for difficult injection molding applications  
Easy colorability with proper MB (PE, PP, etc. based).

**Process Method :** Injection/multi injection molding

**Uses :** Industrial applications, personal care, toys, consumer goods

	Value	Unit	Standard
<b>Physical</b>			
Hardness	65	SHORE A	ISO 868 (3 second)
Density	0,9	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	2,4	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	3,7	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	7	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	650	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	33	N/mm	ISO 34-1 Method B
<b>Aging</b>			
Compression Set (72h/23°C)	34	%	ISO 815
<b>Environmental Resistance</b>			
Ozone	Excellent		
Water	Excellent		
Alcohol	Excellent		



Ravago Petrokimya Uretim A.S.



**ENSOFT SX-400-65A**

**ENSOFT-S**

---

Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

---

**Drying Condition**

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

---

**Molding Condition (°C)**

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

