



**ENSOFT SX-626-67A-T2-CM**

**ENSOFT-S**

**Product Description :** This polyolefin based thermoplastic elastomer (SEBS) compound is medium mineral filled, completely recyclable and suitable for automotive interior applications with low fogging and odour requirements.

**Additive Packages :** T / Heat and UV stabilizer  
/

**Key Features :** Low fogging and odour  
Excellent ozone, UV and weathering resistance  
Rubberlike elasticity in a wide temperature range  
Easy colorability with proper MB (PE, PP, etc. based)

**Process Method :** Injection, multi-injection, co-injection molding

**Uses :** Automotive applications especially car mat

	Value	Unit	Standard
<b>Physical</b>			
Hardness	67	SHORE A	ISO 868 (3 second)
Density	0,98	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	1,8	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	2,8	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	9,5	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	>700	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	30	N/mm	ISO 34-1 Method B
<b>Aging</b>			
Compression Set (72h/23°C)	23	%	ISO 815
Compression Set (22h/70°C)	40	%	ISO 815
<b>Thermal</b>			
Fogging ( 100°C, 3 hr , post test condition 16 hr)	92	%	DIN 75201 Method A,ISO 6452,SAE J1756
Fogging ( 100°C, 3 hr , post test condition 1 hr)	88	%	DIN 75201 Method A,ISO 6452,SAE J1756



Ravago Petrokimya Uretim A.S.



**ENSOFT SX-626-67A-T2-CM**

**ENSOFT-S**

---

Fogging ( ( 100°C, 16 hr , post test condition 4 hr)	0,8	mg	PV3015
--	-----	----	--------

---

**Environmental Resistance**

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

---

**Drying Condition**

Drying Time(hr)	Not required
Drying Temperature(C)	Not required

---

**Molding Condition (°C)**

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

