



ENSOFT TM-300-55A

ENSOFT-T

Product Description :	This polyolefin based thermoplastic elastomer (SBS) compound is unfilled, high performance and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery.
Additive Packages :	H / Heat stabilizer /
Key Features :	Ozone and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. based).
Process Method :	Injection/multi injection molding
Uses :	Injection/multi injection molding

	Value	Unit	Standard
Physical			
Hardness	55	SHORE A	ISO 868 (3 second)
Density	0,92	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	1,4	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	2,3	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	4,2	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	800	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	32	N/mm	ISO 34-1 Method B

Environmental Resistance

Water	Excellent
-------	-----------

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Molding Condition (°C)



Ravago Petrokimya Uretim A.S.



ENSOFT TM-300-55A

ENSOFT-T

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

