



**RAVATECH RO24960A**

**RAVATECH**

**Product Description :** This polar thermoplastic elastomer compound is specifically designed for overmolding with different polar substrates and their blends. RAVATECH® series can be processed with conventional thermoplastics machineries and is fully recyclable.

**Additive Packages :** T / Heat and UV stabilizer  
/

**Key Features :** Adhesion to various polar substrates and their blends  
Rubberlike elasticity in a wide temperature range  
Easy colorability with proper MB  
Good chemical and oil resistance

**Process Method :** Injection, multi-injection, co-injection molding

**Uses :** Soft touch grips, handles, consumer goods, home&kitchen appliances, automotive

	Value	Unit	Standard
<b>Physical</b>			
Hardness	60	SHORE A	ISO 868 (3 second)
Density	1,10	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	1,7	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	3	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	6,5	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	660	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	27	N/mm	ISO 34-1 Method B
Adhesion to ABS	5 (B)	N/mm	VDI 2019
Adhesion to PC	5 (B/D)	N/mm	VDI 2019
<b>Drying Condition</b>			
Drying Time(hr)	2-3		
Drying Temperature(°C)	60-80		
<b>Molding Condition (°C)</b>			
1st Zone (hopper)(°C)	190 - 200		
2nd Zone(°C)	190 - 210		



Ravago Petrokimya Uretim A.S.



**RAVATECH RO24960A**

**RAVATECH**

---

3rd Zone(°C)	200 - 220
Nozzle(°C)	210 - 220
Melt Temperature(°C)	200 - 220
Mold Temperature(°C)	30-70
Max Allowable Melt Temperature(°C)	230

