



# Ravathane R130A75

## Ravago Manufacturing Turkey - Thermoplastic Polyurethane Elastomer

(Polyester)

### General Information

#### Product Description

Description: Product is based on standard grade saturated polyester and has strong resilience and tear resistance, excellent abrasion resistance, higher resistance to hydrolysis failure and oxidation, good stability towards solvents and light.

Application: Compounding, working shoes, transparent parts etc.

#### General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Features	• Abrasion Resistant • Good Tear Strength	• Hydrolysis Resistant • Oxidation Resistant	• Resilient
Uses	• Compounding	• Footwear	• Transparent Parts
Forms	• Pellets		
Processing Method	• Injection Molding		

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm <sup>3</sup>	ISO 1183/A
Mechanical	Nominal Value	Unit	Test Method
Abrasion Resistance	35.0	mm <sup>3</sup>	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	4.00	MPa	ISO 37
Tensile Stress (300% Strain)	7.00	MPa	ISO 37
Tensile Stress (Yield)	30.0	MPa	ISO 37
Tensile Elongation (Break)	650	%	ISO 37
Tear Strength <sup>2</sup>	70.0	kN/m	ISO 34-1
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	75		ISO 868

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	80 to 100	°C
Rear Temperature	170	°C
Middle Temperature	180	°C
Front Temperature	185	°C
Nozzle Temperature	190	°C
Injection Pressure	65.0	MPa

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Method Bb, Angle (Nicked)