



RAVATHANE®

Technical Data Sheet

Ravathane® 150 A75

Description: Non- plasticized thermoplastic polyurethane based on special polyester that having non blooming properties, having strong resilience and tear resistance, excellent abrasion resistance, higher resistance to hydrolysis failure and oxidation, good stability towards solvents and light.

Application: Injection molding.

Feature: Non-blooming

Typical Properties

PROPERTIES	TEST METHOD	UNITS	VALUES
Hardness	ISO 868	Shore A	75
Density	ISO 1183-1 A	g/cm ³	1,21
Tensile stress at:			
-100% elongation	ISO 37	MPa	4,2
-300% elongation	ISO 37	MPa	7,0
Tensile strength at break	ISO 37	MPa	30
Elongation at break	ISO 37	%	1000
Tear strength	ISO 34-1 B/b	N/mm	80
Abrasion resistance	ISO 4649	mm ³	60

Properties have been tested on injection molded plaques conditioned 24 hours at room temperature.

Application Guideline (Injection Molding)

Nozzle (°C)	Metering (°C)	Compression (°C)	Feed (°C)
180-190	185-195	185-195	175-185

Before processing, the pellets have to be dried at 80-90°C for 2-4 hours. Maximum moisture content should be below 0.04%.